



Technical Data

Crema Marfil

TYPE: Marble

ORIGIN: Pinoso, Spain

PHYSICO-MECHANICAL PROPERTIES

Compression strenght	122,84 MPa
Bending strenght	19,41 MPa
Volumetric weight	2,72 gm/cm ³
Friction wear resistance	0,35 mm
Porosity	10.04 %
Knoop micro-hardness	1774,5 MPa
Absorption coefficient	0.15 %
Impact test (minimum height)	42 cm

RECOMMENDED APPLICATIONS

Cladding, flooring, interior decoration.

Note: This technical data is from the Crema Marfil Coto variation. This technical data is only representative. Please do not consider it as 100% accurate or extremely updated.

Source: Incom Pastor